


CHEMICAL COMPATIBILITY OF COMMON FINISHING MATERIALS

Poly Urthane
 Acrylic Enamel
 Epoxy Enamel
 Alkyd Enamel
 Acrylic Laquer
 Buterate Dope
 Nitrate Dope
 Aero Gloss Dope
 Dupont 305
 Poly Resin
 Vinal Spackle



OVER

UNDER

Vinal Spackle	C	N	C	C	C	C	C	C	C	C	C
Poly Resin	C	C	C	C	C	C	C	C	C	C	C
Dupont 305	C	N	C	N	C	C	C	C	C	C	C
Aero Gloss Dope	C	C	C	C	N	C	C	C	C	C	C
Nitrate Dope	C	C	C	C	C	C	C	C	C	C	C
Buterate Dope	C	N	C	N	N	C	C	C	C	C	C
Acrylic Laquer	C	N	C	N	C	N	C	C	C	C	C
Alkyd Enamel	C	N	C	N	C	N	N	C	N	N	N
Epoxy Enamel	C	N	C	N	C	N	C	C	C	C	C
Acrylic Enamel	C	N	C	N	C	N	N	C	N	C	N
Poly Urthane	C	N	C	N	C	N	C	C	C	C	C

A "C" in a column indicates that the combination is compatible; an "N" indicates that the combination is not compatible.

Example: Vinal Spackle is compatible over Poly Resin. (Find "Vinal Spackle" in the "OVER" section and read down to "Poly Resin." Compatibility is the intersection of the two.)

Example: Vinal Spackle is not compatible when put under Poly Resin. (Find Vinal Spackle in the "under" section and read across to Poly Resin.)